


Pyrocrete[®] 241

Proven Protection Under Fire



History of Performance Excellence

Over 30 years of successful case histories and more than 100 million square feet of structural steel protected worldwide.

Since the late 1970's Pyrocrete 241 has been the industry leader in cementitious fireproofing and continues to be the most specified and highly regarded cementitious fireproofing material in the world. With over 30 years of unparalleled performance, it is the global benchmark for high performance cementitious fireproofing in the refining and petrochemical industries.

Pyrocrete 241 is synonymous with high quality. Pyrocrete 241 is manufactured using only the highest quality raw materials with strict QA/QC protocols all under the UL follow up service to ensure the highest quality product for our customers worldwide.

Pyrocrete 241 Performance Advantages

Pyrocrete 241 is a high density, exterior grade, heavy duty, cementitious fireproofing material ideal for use in industrial and petrochemical environments. Pyrocrete 241 can provide 1 to 4 hour(s) of fire protection for structural steel, vessel skirts, bulkheads, LPG vessels, LNG terminals or to upgrade the fire resistance of existing concrete.

Pyrocrete 241 is suitable for both field and shop applications when applied by our published application procedures.

The superior physical properties of Pyrocrete 241 promote high durability when handling, during construction, and while in service.

Features and Benefits

PRODUCT FEATURE	PERFORMANCE BENEFIT
55 PCF Density (avg.)	Harder, more durable material. Tough surface suitable for harsh exterior exposures.
High Impact & Compressive Strength	Damage resistant during transportation, construction, and throughout service life.
High Bond Strength	Prevents failures from disbondment and cracking which lowers repair & maintenance costs.
Industry Leading Ratings	Lower installation & material costs.
1/5 The Weight of Concrete	Weight savings, reducing overall construction, transportation & installation costs.

Applications

- > Refineries
- > Chemical Plants
- > Gas Plants
- > LPG Vessels
- > LNG Facilities
- > Pharmaceutical Facilities
- > Pulp and Paper Mills
- > Nuclear Power Plants
- > Conventional Power Plants
- > Biomedical Facilities
- > Factories and Warehouses
- > Commercial Buildings

PIPERACK SUPPORT PROTECTED WITH PYROCRETE 241, WITHSTANDS HYDROCARBON FIRE.



PYROCRETE 241 APPLIED OFFSITE AND TRANSPORTED TO JOBSITE.




Rigorously Tested, Certified & Proven

Pyrocrete 241 has a proven track record of performance when subjected to the harshest environmental conditions and the extreme heat of hydrocarbon fire.

Pyrocrete 241 has been tested and certified for a variety of exposures, with successful performance in actual hydrocarbon fires in refining and petrochemical facilities around the world.

Certifications & Listings:

- > UL (Underwriter's Laboratories) 
 - UL 1709 Hydrocarbon Ratings
 - UL 263 (ASTM E-119) Cellulosic Ratings
- > Lloyd's Register of Shipping
 - ISO 22899-1 Jet Fire Ratings
- > BS-476 Hydrocarbon Ratings
 - HP/A: 30-305
- > FM Global (Factory Mutual)
 - LPG Vessel Approvals
 - Structural Steel Approvals

UL Environmental Testing:

Pyrocrete 241 has successfully passed the following exposures simulating 20+ year exterior life cycle:

- > Accelerated Aging
- > High Humidity
- > Industrial Atmosphere
- > Salt spray
- > Combination Wet / Freeze / Dry Cycling


Performance Testing

Pyrocrete 241 has successfully passed the following independent third party test programs:


- > Jet Fire Impingement
- > Hose Stream Endurance
- > Cryogenic Exposure
- > 3 Bar Overblast

PHYSICAL PROPERTIES	TEST PROCEDURE	TYPICAL RESULTS
Density	ASTM E605	55 PCF (.88 g/cm ³)
Bond Strength	ASTM E736	4,871 psf (233 kPa)
Compressive Strength	ASTM E761	817 psi (5,633 kPa)
Impact Resistance	ASTM E760	Pass
Deflection	ASTM E759	Pass
Corrosion	ASTM E937	0.00 g/mm
Flame Spread	ASTM E84	0
Smoke Development	ASTM E84	0
Average Flexural Strength	ASTM D790	502 psi (3,461 kPa)
Insulation "K" Factor (@ 75°F [24°C])	ASTM C177	0.87 BTU in/hr ft ² °F (0.125 W/m ² K)
Coverage per 50 lb (22.7 kg) bag	-	14.3 ft ² (1.3 m ²)

Pyrocrete 241
Contour Design



Pyrocrete 241
Box Design



JET FIRE IMPINGEMENT



CRYOGENIC EXPOSURE



GLOBAL COATINGS LEADERS™

RIGHT PEOPLE · RIGHT PRODUCTS · RIGHT LOCATIONS



GLOBAL MANUFACTURING PLANTS

CARBOLINE COMPANY
GLOBAL HEADQUARTERS
2150 SCHUETZ ROAD
ST. LOUIS, MO 63146 USA
PH: +1-314-644-1000
WWW.CARBOLINE.COM

ARGENTINA - BUENOS AIRES
EINSTEIN 1095
PARQUE INDUSTRIAL OKS
GARÍN PROV. DE BUENOS
AIRES, ARGENTINA
PHONE: 54-3327-44-2222
FAX: 54-3327-44-2223

AUSTRALIA - BRISBANE
7 PRODUCTION AVE
ERNEST JUNCTION
QUEENSLAND 4214
AUSTRALIA
PHONE: +61 7 3287 0222
FAX: +61 7 5594 9093

CANADA - ONTARIO
420 TAPSCOTT ROAD UNIT 5
SCARBOROUGH, ONTARIO
M1B 1Y4, CANADA
PHONE: 416-292-2361
FAX: 416-298-5887

CHINA - DALIAN
HOU SHI CUN, DA WEI JIA
ZHEN
JIN ZHOU DISTRICT
DALIAN, CHINA 116110
PHONE: 86-411-8789-8441,
8442, 8443, 8444
FAX: 86-411-8789-8445

INDIA - CHENNAI
NO. 356 & 357 SIDCO
INDUSTRIAL ESTATE
AMBATTUR,
CHENNAI 600 098
INDIA
PHONE: 91-22-28500321
FAX: 91-22-28500323

INDIA - MAHARASHTRA
GUT NO. 300
VILLAGE MUSSARNE
BHIWANDI WADA ROAD,
TALUKA WADA,
DISTRICT PALGHAR,
MAHARASHTRA
INDIA

ITALY - ALGERO
VIA MILANO 150
20093 COLOGNO MONZESE
(MI), ITALY
PHONE: 3902-25 3751
FAX: 3902-25 37560

JAPAN - AMAGASAKI
TERAMOTO UNYU SOKO CO.,
LTD 17
MINAMIHATSUSHIMA-CHO,
AMAGASAKI, 660-0833 JAPAN
PHONE: 81-3-3643-4501
FAX: 81-3-3643-2951

MALAYSIA - KUALA LUMPUR
LOT 37631-37632 JALAN 6/37A
TAMAN BUKIT MALURI
INDUSTRIAL AREA
KEPONG 52100,
KUALA LUMPUR, MALAYSIA
PHONE: 603-6277-9575
FAX: 603-6277-4645

NEW ZEALAND - TAURANGA
91-111 OROPI ROAD
GREERTON
TAURANGA
NEW ZEALAND
PHONE: +64 7 5411 221
FAX: +64 7 541 1310

NORWAY - LIERSTRANDA
P.O. BOX 593
3412 LIERSTRANDA, NORWAY
PHONE: 47-32-857300
FAX: 47-32-857301

PUERTO RICO - SAN LORENZO
URB. APONTE #5
SAN LORENZO, PUERTO RICO
00754
PHONE: 787-736-4221
FAX: 787-736-53133

SAUDI ARABIA - DAMMAM
1ST INDUSTRY CITY, 28TH
STREET
P.O. BOX 1050
DAMMAM 31431,
KINGDOM OF SAUDI ARABIA
PHONE: +966 3 847 3044
FAX: +966 3 847 3689

SOUTH AFRICA - JOHANNESBURG
8 CRESSET ROAD
MIDRAND INDUSTRIAL PARK
JOHANNESBURG,
SOUTH AFRICA
PHONE: 27-11-2545500
FAX: 27-11-310-2872

SOUTH KOREA - BUSAN
43-1, JINYOUNG-RI
GREERTON
JINYOUNG-EUB
KIMHAE-CITY, 621-800
KYOUNGSANGNAMDO, KOREA
PHONE: 82-55-343-6441/5
FAX: 82-55-343-6414

TURKEY - BURSA
ALI OSMAN SONMES CAD.
NO:4
BURSA, DOSAB 16369 TURKEY
PHONE: 90-224-261-0537

UAE - DUBAI
P.O. BOX 3034
DUBAI, UAE
PHONE: 971-4-347-0460
FAX: 971-4-347-0242

USA - DAYTON
95 AIRPARK VISTA BLVD.
DAYTON, NV 89403
PHONE: 775-246-0760
FAX: 775-246-0763

USA - GREEN BAY
614 ELIZABETH ST
GREEN BAY, WI 54302
PHONE: 920-437-6561
FAX: 920-437-8546

USA - LAKE CHARLES
900 OPELOUSAS STREET
LAKE CHARLES, LA 70601
PHONE: 337-433-0605
FAX: 337-439-0380

USA - LOUISA
321 DUKE ST.
LOUISA VA 23093
PHONE: 540-967-5119
FAX: 540-967-5120

VENEZUELA - VALENCIA
URBANIZACION INDUSTRIAL
"EL TIGRE"
AVENIDA PRINCIPAL
GALPÓN "H"
VALENCIA EDO. CARABOBO
VENEZUELA
PHONE: 58-245-4000400
FAX: 58-245-5642011

