

## SELECTION & SPECIFICATION DATA

<b>Generic Type</b>	Waterborne Acrylic
<b>Description</b>	Versatile high performance finish with excellent corrosion resistance and exterior weathering properties, as well as suitability for interior and mild environments.
<b>Features</b>	<ul style="list-style-type: none"> <li>• Multi-purpose interior/exterior coating</li> <li>• Excellent color and gloss retention</li> <li>• Single component</li> <li>• Outstanding corrosion protection</li> <li>• Low odor, low VOC*</li> </ul> <p>*Meets stringent VOC regulations including SCAQMD (South Coast Air Quality Management District for Industrial Maintenance - California)</p>
<b>Color</b>	1864 (White), C900 (Black), 0754 (Grey), 5555 (Safety Red), 6666 (Safety Yellow). Other colors are available on request. Contact your Carboline Representative for availability.
<b>Finish</b>	Semi-Gloss
<b>Primer</b>	Acrylics, Alkyds, Epoxies, Inorganic and Organic Zincs and others as recommended under Substrates & Surface Preparation. A mist coat may be required to minimize bubbling over Inorganic Zinc primers.
<b>Dry Film Thickness</b>	<p>2 - 3 mils (51 - 76 microns) per coat</p> <p><b>Do not exceed 3.0 mils in a single coat.</b></p>
<b>Solids Content</b>	By Volume 38% +/- 2%
<b>Theoretical Coverage Rate</b>	<p>610 ft<sup>2</sup>/gal at 1.0 mils (15.0 m<sup>2</sup>/l at 25 microns)</p> <p>305 ft<sup>2</sup>/gal at 2.0 mils (7.5 m<sup>2</sup>/l at 50 microns)</p> <p>203 ft<sup>2</sup>/gal at 3.0 mils (5.0 m<sup>2</sup>/l at 75 microns)</p> <p>Allow for loss in mixing and application.</p>
<b>VOC Values</b>	<p><b>As Supplied</b> : 0.5lbs/gal (60 g/l)</p> <p>These are nominal values and may vary slightly with color.</p> <p><b>EPA Method 24</b>: 0.8 lbs/gal (100 g/l) (Calculated minus water and exempt solvents)</p>
<b>Dry Temp. Resistance</b>	<p>Continuous: 235°F (113°C)</p> <p>Non-Continuous: 325°F (163°C)</p> <p>Slight discoloration and loss of gloss is observed above 200 F (93 C).</p>
<b>Limitations</b>	Apply and cure at temperatures of 50°F and above for 24 hours.

## SUBSTRATES & SURFACE PREPARATION

<b>General</b>	Surfaces must be clean and dry. Employ adequate methods to remove dirt, dust, oil and all other contaminants that could interfere with adhesion of the coating.
<b>Steel</b>	SSPC-SP6 with a 1.0-2.0 mil (25-50 micron) surface profile for maximum protection. SSPC-SP2 or SP3 as minimum requirement. Prime with specific Carboline primers as recommended by your Carboline Sales Representative.

# Carbocrylic® 3359 MC

## PRODUCT DATA SHEET



### SUBSTRATES & SURFACE PREPARATION

<b>Galvanized Steel</b>	SSPC-SP1. Prime with Carbocrylic® 120 or others as recommended by your Carboline Sales Representative.
<b>Concrete or CMU</b>	<b>Concrete:</b> Must be cured 28 days at 75°F (24°C) and 50% relative humidity or equivalent. Laitance, form oils, curing agents and hardeners must be removed by suitable method before coating application. Prime with Carbocrylic 120. <b>CMU:</b> Mortar joints should be thoroughly cured for a minimum of 15 days at 75°F (24°C) and 50% relative humidity or equivalent. Prime with a latex block filler.
<b>Drywall &amp; Plaster</b>	Joint compound and plaster should be fully cured prior to coating application. Prime with Carbocrylic 120.
<b>Previously Painted Surfaces</b>	Lightly sand or abrade to roughen surface and degloss the surface. Existing paint must attain a minimum 3A rating in accordance with ASTM D3359 "X-Scribe" adhesion test. Prime with Carbocrylic 120 or others as recommended by your Carboline Sales Representative.
<b>Wood</b>	Lightly sand with fine sandpaper and remove dust. Prime with Carbocrylic 120.

### PERFORMANCE DATA

All test data was generated under laboratory conditions. Field testing results may vary.

Test Method	System	Results
ASTM B117 Salt Fog	Blasted Steel 1 ct. IOZ 1 ct. 3359	No blistering, rusting or rust creepage at scribe after 1500 hours
ASTM D1653 Water Vapor Transmission	1 ct. 3359	Water Vapor Permeance (WVP) of 3.94 U.S. Perms
ASTM D3359 Adhesion	Blasted Steel 1 ct. 3358 1 ct 3359	5A
ASTM D3363 Pencil Hardness	1 ct. Acrylic Pr. 2 cts. 3359	5B
ASTM D4060 Abrasion	1 ct. Acrylic Pr 2 cts. 3359	185 mg. loss. 3000 cycles, CS10 Wheel
ASTM D4213 Scrub Resistance	1 ct. 3359	.0235/.0655 Microliters per 100 cycles Wet/Dry Film Volume
ASTM D4541 Adhesion	Stainless Steel 1 ct. 3359	1675 psi (Elcometer)

Test reports based on Carbocrylic 3359.

### MIXING & THINNING

<b>Mixing</b>	Power mix until uniform in consistency. Avoid excessive air entrapment.
<b>Thinning</b>	May be thinned up to 6 oz/gal (5%) with clean, potable water. Areas with cool substrate and warm ambient conditions can experience a surface skinning and separation. Under these conditions, the use of 6-12 oz/gal (5-10%) of Additive 102 assists in the proper film formation at the recommended dry film thickness, without surface skinning. Use of thinners other than those supplied by Carboline may adversely affect product performance and void product warranty, whether expressed or implied.

## APPLICATION EQUIPMENT GUIDELINES

Listed below are general equipment guidelines for the application of this product. Job site conditions may require modifications to these guidelines to achieve the desired results.

<b>Spray Application (General)</b>	Pre-rinse equipment with undiluted Carboline Surface Cleaner 3 followed by clean potable water before spraying. The following spray equipment has been found suitable and is available from manufacturers such as Binks, DeVilbiss and Graco.
<b>Conventional Spray</b>	Pressure pot equipped with dual regulators, ½" I.D. minimum material hose, .086" I.D. fluid tip and appropriate air cap.
<b>Airless Spray</b>	Pump Ratio: 30:1 (min.)* Pump Ratio: 45:1 for two or more guns GPM Output: 3.0 (min.) Material Hose: 3/8" I.D. (min.) Tip Size: .017-.019" Output PSI: 1800-2100 Filter Size: 60 mesh *PTFE packings are recommended and available from the pump manufacturer. For ease of application, remove the pickup tube and immerse the lower unit directly into the material.
<b>Brush &amp; Roller (General)</b>	Multiple coats may be required to achieve desired appearance, hiding and recommended dry film thickness. Avoid excessive re-brushing or re-rolling.
<b>Brush</b>	Use a synthetic bristle brush.
<b>Roller</b>	Use a short-nap synthetic roller cover with solvent resistant core. For rough surfaces, use a 3/8" woven nap synthetic roller.

## APPLICATION CONDITIONS

Condition	Material	Surface	Ambient	Humidity
Minimum	50°F (10°C)	50°F (10°C)	50°F (10°C)	0%
Maximum	105°F (41°C)	130°F (54°C)	110°F (43°C)	85%

**Do not apply when the surface temperature is less than 5°F (3°C) above the dew point. Do not apply if temperatures are expected to drop below 50°F (10°C) within 24 hours of application.** Special application techniques may be required above or below normal application conditions.

## CURING SCHEDULE

Surface Temp.	Dry to Handle	Dry to Topcoat
50°F (10°C)	3 Hours	3 Hours
75°F (24°C)	2 Hours	2 Hours
90°F (32°C)	1 Hour	1 Hour

These times are based on a 2.0-3.0 mil (50-75 micron) dry film thickness. High film thicknesses, insufficient ventilation, high humidity or cooler temperatures will require longer cure times.

The acrylic film forming process may require several weeks at 75 F (24 C) with proper ventilation to develop adhesion and water resistance. High humidity, high film thickness, insufficient ventilation or cooler temperatures will lengthen the Dry to Handle and Dry to Topcoat times due to slower water evaporation rate. Waterborne acrylics are sensitive to moisture during early cure and are susceptible to handling damage.

# Carbocrylic® 3359 MC

## PRODUCT DATA SHEET



### CLEANUP & SAFETY

<b>Cleanup</b>	Use clean potable water followed with suitable solvent to dry equipment. In case of spillage, absorb and dispose of in accordance with local applicable regulations.
<b>Safety</b>	Read and follow all caution statements on this product data sheet and on the SDS for this product. Employ normal workmanlike safety precautions. Keep container closed when not in use.
<b>Ventilation</b>	When used as a tank lining or in enclosed areas, thorough air circulation must be used during and after application until the coating is cured. The ventilation system should be capable of preventing the solvent vapor concentration from reaching the lower explosion limit for the solvents used. User should test and monitor exposure levels to insure all personnel are below guidelines. If not sure or if not able to monitor levels, use MSHA/NIOSH approved supplied air respirator.

### PACKAGING, HANDLING & STORAGE

<b>Shelf Life</b>	36 months at 75°F (24°C) *Shelf Life: (actual stated shelf life) when kept at recommended storage conditions and in original unopened containers.
<b>Storage Temperature &amp; Humidity</b>	40° -110°F (4°-43°C) 0-95% Relative Humidity
<b>Storage</b>	Store indoors. KEEP FROM FREEZING.
<b>Shipping Weight (Approximate)</b>	1 Gallon - 11 lbs (5 kg) 5 Gallons - 51 lbs (23 kg) 50 Gallons - 525 lbs (239 kg)
<b>Flash Point (Setaflash)</b>	>200°F (93°C)

### WARRANTY

To the best of our knowledge the technical data contained herein is true and accurate on the date of publication and is subject to change without prior notice. User must contact Carboline to verify correctness before specifying or ordering. No guarantee of accuracy is given or implied. Carboline warrants our products to be free of manufacturing defects in accord with applicable Carboline quality control procedures. THIS WARRANTY IS NOT VALID WHEN THE PRODUCT IS NOT: (1) APPLIED IN ACCORDANCE WITH CARBOLINE'S SPECIFICATIONS, AND/OR (2) PROPERLY STORED, CURED, AND USED UNDER NORMAL OPERATING CONDITIONS. Carboline assumes no responsibility for coverage, performance, injuries, or damages resulting from use of the product. If this product is found not to perform as specified upon inspection by a Carboline representative during the warranty period, Carboline's sole obligation, if any, is to replace the Carboline product(s) proven to be defective or refund the purchase price thereof, at Carboline's sole option. Carboline shall not be liable for any other losses or damages. This warranty excludes (1) labor and costs of labor for the application or removal of any product, and (2) any incidental or consequential damages, whether based on breach of express or implied warranty, negligence, strict liability or any other legal theory. NO OTHER WARRANTY OR GUARANTEE OF ANY KIND IS MADE BY CARBOLINE, EXPRESS OR IMPLIED, STATUTORY, BY OPERATION OF LAW, OR OTHERWISE, INCLUDING MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. All of the trademarks referenced above are the property of Carboline International Corporation unless otherwise indicated. The whole text of this Product Data Sheet, as well as the documents derived from it, have been written in English, and for legal purposes the English version shall prevail.