

## SELECTION & SPECIFICATION DATA

<b>Generic Type</b>	Solvent Based Organic Zinc-Rich Epoxy
<b>Description</b>	Low VOC organic zinc epoxy steel primer with quick cure-to-topcoat characteristics for in-shop applications and quick turnaround requirements in the field. Carbozinc 858 DOT has very good adhesion and undercutting resistance and is excellent for use as a corrosion resistant primer for a variety of applications.
<b>Features</b>	<ul style="list-style-type: none"> <li>• Meets SSPC Paint System 20</li> <li>• Low temperature cure down to 35°F (2°C)</li> <li>• Protects against undercutting corrosion</li> <li>• Available in ASTM D520, Type III zinc version</li> <li>• May be applied with standard airless or conventional spray equipment</li> <li>• VOC compliant to current AIM regulations</li> </ul>
<b>Color</b>	Green (0300)
<b>Finish</b>	Matte
<b>Primer</b>	Self Priming
<b>Dry Film Thickness</b>	3 - 5 mils (76 - 127 microns) per coat Dry film thickness in excess of 8.0 mils (200 microns) per coat is not recommended.
<b>Total Zinc Dust in Dry Film</b>	By Weight: 81%
<b>Solids Content</b>	By Volume 64% +/- 2%
<b>Theoretical Coverage Rate</b>	1027 ft <sup>2</sup> /gal at 1.0 mils (25.2 m <sup>2</sup> /l at 25 microns) 342 ft <sup>2</sup> /gal at 3.0 mils (8.4 m <sup>2</sup> /l at 75 microns) 205 ft <sup>2</sup> /gal at 5.0 mils (5.0 m <sup>2</sup> /l at 125 microns) Allow for loss in mixing and application.
<b>VOC Values</b>	<b>As Supplied</b> : 2.5 lbs./gal (303 g/l) Thinner 2 : 8 oz/gal: 2.8 lbs./gal (335 g/l) Thinner 33 : 8 oz/gal: 2.82 lbs./gal (338 g/l) These are nominal values. *Use Thinner #76 for projects requiring non-photochemically reactive solvents.
<b>Dry Temp. Resistance</b>	Continuous: 300°F (149°C) Non-Continuous: 350°F (177°C)
<b>Topcoats</b>	May be coated with Acrylics, Epoxies, or Polyurethanes depending on exposure and need.

## SUBSTRATES & SURFACE PREPARATION

<b>General</b>	Surfaces must be clean and dry. Employ adequate methods to remove dirt, dust, oil and all other contaminants that could interfere with adhesion of the coating.
<b>Steel</b>	SSPC-SP6 with a 1.0-3.0 mil (25-75 micron) surface profile. SSPC-SP2 or SP3 for touch-up.

### MIXING & THINNING

<b>Mixing</b>	Power mix Part A completely. Then slowly sift in the zinc filler under agitation. Power mix Part B separately and add slowly to the mixture. Pour mixture through a 30 mesh screen. DO NOT MIX PARTIAL KITS. <b>Tip:</b> Sifting zinc through a window screen will aid in the mixing process by breaking up or catching dry zinc lumps.
<b>Thinning</b>	Normally not required but may be thinned up to 8 oz/gal (10%) with Thinner #2 or Thinner #76. In hot or windy conditions, may be thinned up to 8 oz/gal with Thinner #33. Use of thinners other than those supplied by Carboline may adversely affect product performance and void product warranty, whether expressed or implied.
<b>Ratio</b>	<u>.80 Gal. Kit</u> Part A: .35 gallons Part B: .20 gallons Zinc Filler: 14.6 lbs <u>4.00 Gal Kit</u> Part A: 1.75 gallons Part B: 1 gallon Zinc Filler: 73 lbs.
<b>Pot Life</b>	4 Hours at 75°F (24°C) and less at higher temperatures. Pot life ends when coating loses body and begins to sag.

### APPLICATION EQUIPMENT GUIDELINES

Listed below are general equipment guidelines for the application of this product. Job site conditions may require modifications to these guidelines to achieve the desired results.

<b>Spray Application (General)</b>	The following spray equipment has been found suitable and is available from manufacturers. Keep material under mild agitation during application.
<b>Conventional Spray</b>	Agitated pressure pot equipped with dual regulators, 3/8" I.D. minimum material hose, 0.070" I.D. fluid tip and appropriate air cap.
<b>Airless Spray</b>	Pump Ratio: 30:1 (min.)* GPM Output: 3.0 (min.) Material Hose: 3/8" I.D. (min.) Tip Size: 0.017-0.023" Output PSI: 2000-2200 Filter Size: 60 mesh *PTFE packings are recommended and available from the pump manufacturer.
<b>Brush</b>	For small areas and touch-up only. Use medium bristle brush and avoid rebrushing.
<b>Roller</b>	Not recommended.

## APPLICATION CONDITIONS

Condition	Material	Surface	Ambient	Humidity
Minimum	40°F (4°C)	35°F (2°C)	35°F (2°C)	0%
Maximum	90°F (32°C)	120°F (49°C)	110°F (43°C)	95%

Industry standards are for the substrate temperatures to be 5°F (3°C) above the dew point. This product simply requires the substrate temperature to be above the dew point. Condensation due to substrate temperatures below the dew point can cause flash rusting on prepared steel and interfere with proper adhesion to the substrate. Special application techniques may be required above or below normal application conditions.

## CURING SCHEDULE

Surface Temp.	Dry to Handle	Dry to Topcoat
35°F (2°C)	8 Hours	8 Hours
50°F (10°C)	5 Hours	5 Hours
75°F (24°C)	2 Hours	2 Hours
100°F (38°C)	1 Hour	1 Hour

These times are based on 50% relative humidity and 3.0 mil (75 micron) dry film thickness. Higher film thickness, insufficient ventilation or cooler temperatures will require longer cure times and could result in solvent entrapment and premature failure. Dry to touch at 75°F (24°C) in 30 minutes.

**Specific topcoat products can be used in a much shorter re-coat interval. Consult Carboline for recommendations and test results.**

**Maximum Recoat:** Unlimited.

Must have a clean, dry surface for topcoating. "Loose" chalk or salts must be removed in accordance with good painting practice. Consult Carboline Technical Service for specific information.

## CLEANUP & SAFETY

<b>Cleanup</b>	Use Thinner #2 or Acetone. In case of spillage, absorb and dispose of in accordance with local applicable regulations.
<b>Safety</b>	Read and follow all caution statements on this product data sheet and on the SDS for this product. Employ normal workmanlike safety precautions.
<b>Ventilation</b>	When used in enclosed areas, thorough air circulation must be used during and after application until the coating is cured. The ventilation system should be capable of preventing the solvent vapor concentration from reaching the lower explosion limit for the solvents used. In addition to ensuring proper ventilation, appropriate respirators must be used by all application personnel.
<b>Caution</b>	This product contains flammable solvents. Keep away from sparks and open flames. all electrical equipment and installations should be made and rounded in accordance with the National Electric Code. In areas where explosion hazards exist workers should be required to use non-ferrous tools and wear conductive and non-sparking shoes.

## PACKAGING, HANDLING & STORAGE

<b>Shelf Life</b>	Part A: Min. 24 months at 75°F (24°C) Part B: Min. 24 months at 75°F (24°C) Zinc Filler: 24 months at 75°F (24°C)  *Shelf Life: (actual stated shelf life) when kept at recommended storage conditions and in original unopened containers.
-------------------	---

### PACKAGING, HANDLING & STORAGE

<b>Storage Temperature &amp; Humidity</b>	40° – 110°F (4° - 43°C). 0-95% Relative Humidity
	This product is solvent based and not affected by excursions below these published storage temperatures down to 10°F for a duration of no more than 14 days. Always inspect the product prior to use to make sure it is smooth and homogeneous when properly mixed.
<b>Storage</b>	Store Indoors
<b>Shipping Weight (Approximate)</b>	.80 Gallon Kit - 22 lbs (10 kg)
	4.00 Gallon Kit - 105 lbs (48 kg)
<b>Flash Point (Setaflash)</b>	Part A: 48°F (9°C)
	Part B: 38°F (3°C)
	Zinc Filler: NA

### WARRANTY

To the best of our knowledge the technical data contained herein is true and accurate on the date of publication and is subject to change without prior notice. User must contact Carboline to verify correctness before specifying or ordering. No guarantee of accuracy is given or implied. Carboline warrants our products to be free of manufacturing defects in accord with applicable Carboline quality control procedures. THIS WARRANTY IS NOT VALID WHEN THE PRODUCT IS NOT: (1) APPLIED IN ACCORDANCE WITH CARBOLINE'S SPECIFICATIONS, AND/OR (2) PROPERLY STORED, CURED, AND USED UNDER NORMAL OPERATING CONDITIONS. Carboline assumes no responsibility for coverage, performance, injuries, or damages resulting from use of the product. If this product is found not to perform as specified upon inspection by a Carboline representative during the warranty period, Carboline's sole obligation, if any, is to replace the Carboline product(s) proven to be defective or refund the purchase price thereof, at Carboline's sole option. Carboline shall not be liable for any other losses or damages. This warranty excludes (1) labor and costs of labor for the application or removal of any product, and (2) any incidental or consequential damages, whether based on breach of express or implied warranty, negligence, strict liability or any other legal theory. NO OTHER WARRANTY OR GUARANTEE OF ANY KIND IS MADE BY CARBOLINE, EXPRESS OR IMPLIED, STATUTORY, BY OPERATION OF LAW, OR OTHERWISE, INCLUDING MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. All of the trademarks referenced above are the property of Carboline International Corporation unless otherwise indicated. The whole text of this Product Data Sheet, as well as the documents derived from it, have been written in English, and for legal purposes the English version shall prevail.