

SELECTION & SPECIFICATION DATA

Description	Two-component, self-leveling, polyurethane sealant. It exhibits excellent flexibility with moderate hardness and good chemical resistance to organic acids, alkalis and most solvents. Uses: can be used in conjunction with all lining systems in a wide range of applications. All high movement joints: isolation, expansion or control Thermal shock situations Exterior applications
Features	• Long term abrasion and chemical resistance • Excellent bond strength assures good adhesion • Pourable viscosity allows easy installation to horizontal surfaces • Retains physical properties over a wide temperature range, -20 to 150°F (-29 to 66°C) • Factory proportioned packaging ensures consistent high quality and simplified mixing • Compatible with all Carboline lining systems
Color	0700 (Grey)
Finish	N/A
Primer	After proper surface preparation, 6325 Sealant will attain adhesion to most surfaces without the use of primer.
Coverage Rate	<i>Coverage given in linear ft/gal (linear m/L)</i> <u>3/16" (4.8 mm) Joint Width:</u> 68 ft (5.5 m) @ 1.5" (38 mm) joint depth 51 ft (4.2 m) @ 2" (51 mm) joint depth 41 ft (3.2 m) @ 2.5" (63 mm) joint depth <u>1/4" (6.4 mm) Joint Width:</u> 51 ft (4.2 m) @ 1.5" (38 mm) joint depth 38 ft (3.2 m) @ 2" (51 mm) joint depth 30 ft (2.4 m) @ 2.5" (63 mm) joint depth <u>3/8" (9.5 mm) Joint Width:</u> 34 ft (2.6 m) @ 1.5" (38 mm) joint depth 25 ft (2.1 m) @ 2" (51 mm) joint depth 20 ft (1.6 m) @ 2.5" (63 mm) joint depth Coverages listed are theoretical, actual coverage's may vary based on substrate and site variations.
Topcoats	Not Applicable

SUBSTRATES & SURFACE PREPARATION

General	Ensure the joint is clean, dry and free from contaminants. Cleaning can be carried out with a vacuum and oil free compressed air. All joint facings must possess and open surface with all curing compounds and sealers removed.
----------------	---

SUBSTRATES & SURFACE PREPARATION

Special Instruction

TAPING

Taping should be done after priming to avoid wicking primer under tape on rough surfaces where bonding may be insufficient. Adjacent areas to joint should be masked for neatness. Remove all masking tape immediately after tooling is complete.

BACKING MATERIALS

In deep-jointed areas the sealant penetration should be controlled through the installation of a polyurethane foam rod or polyethylene backer rod. Diameter of the backer rod stock should be one grade larger than the joint width to ensure compression of the backer rod when inserted. Care should be taken to ensure backer rod is not punctured. Where the joint design or depth of joint will not permit the use of joint backing, adhesive-backed polyethylene bond breaker tape must be installed. These materials prevent three-sided adhesion which allows the Sealant to perform to specification. Proper joint dimensions allow for a maximum depth equal to half the joint width.

Minimum ambient and surface temperatures are 60°F/16°C at the time of application. Apply only on clean, sound, properly prepared substrate. Application and curing times are dependent upon ambient conditions. Do not use water or steam in the vicinity of the application. Moisture can seriously affect the working time and properties of the material.

PERFORMANCE DATA

All test data was generated under laboratory conditions. Field testing results may vary.

Test Method	Results
Hardness Shore A	50 (ASTM D-2240)
Joint Movement Capability	+/- 25% (TT-S-00227E)
Percent Elongation	450% (ASTM D-638)
Specification	6325 Sealant meets the requirements of a general purpose sealant
Tensile Strength	250 psi (ASTM C-307)

The above physical properties were measure in accordance with the referenced standards. Samples of the actual system including binder and filler were used as test specimens.

MIXING & THINNING

Mixing

Mixing must be achieved by mechanical means. Mechanical mixing should be done using a heavy-duty, slow-speed drill (80-150 rpm) with a Jiffy Mixer. Pour contents of Component A into a mixing container and premix to assure the suspension of solids. Add Component B and continue to mix to a uniform consistency for a period of approximately two minutes. Avoid high-speed mixing that will entrain air into the mix. Thorough mixing of the two components is required.

APPLICATION PROCEDURES

Application

The Sealant must be applied immediately after mixing. Pour the mixed material directly into the joint. The Sealant is self-leveling and will seek its own level but tooling is necessary to ensure complete edge contact and a completely smooth surface. Use a joint finishing tool.

NOTE: Working time for the material is 40 minutes @ 77°F. (25°C)

APPLICATION CONDITIONS

Condition	Material	Surface	Ambient	Humidity
Minimum	60°F (16°C)	60°F (16°C)	60°F (16°C)	0%
Maximum	85°F (29°C)	110°F (43°C)	85°F (29°C)	80%

Application and curing times are dependent upon ambient conditions. Do not use water or steam in the vicinity of the application, moisture can seriously affect the working time and properties of the material.

CURING SCHEDULE

Surface Temp.	Light Traffic	Tack Free Surface	Ultimate Physical Characteristics
77°F (25°C)	24 Hours	12 Hours	14 Days

CLEANUP & SAFETY

Caution	Both components are skin and eye irritants - avoid contact. The use of a NIOSH/MSHA approved respirator, safety goggles and impervious gloves is recommended. Use only adequate ventilation. In case of contact flush the area with water for 15 minutes and seek medical attention. Wash skin with soap and water.
----------------	---

PACKAGING, HANDLING & STORAGE

Packaging	2 units of part A and 2 poly bags in a box
Shelf Life	24 months in the original, unopened containers
Storage Temperature & Humidity	Store both components between 60-85°F/16-29°C in a dry area. Avoid excessive heat. DO NOT FREEZE
Storage	Store indoors
Shipping Weight (Approximate)	44 pounds

WARRANTY

To the best of our knowledge the technical data contained herein is true and accurate on the date of publication and is subject to change without prior notice. User must contact Carboline to verify correctness before specifying or ordering. No guarantee of accuracy is given or implied. Carboline warrants our products to be free of manufacturing defects in accord with applicable Carboline quality control procedures. THIS WARRANTY IS NOT VALID WHEN THE PRODUCT IS NOT: (1) APPLIED IN ACCORDANCE WITH CARBOLINE'S SPECIFICATIONS, AND/OR (2) PROPERLY STORED, CURED, AND USED UNDER NORMAL OPERATING CONDITIONS. Carboline assumes no responsibility for coverage, performance, injuries, or damages resulting from use of the product. If this product is found not to perform as specified upon inspection by a Carboline representative during the warranty period, Carboline's sole obligation, if any, is to replace the Carboline product(s) proven to be defective or refund the purchase price thereof, at Carboline's sole option. Carboline shall not be liable for any other losses or damages. This warranty excludes (1) labor and costs of labor for the application or removal of any product, and (2) any incidental or consequential damages, whether based on breach of express or implied warranty, negligence, strict liability or any other legal theory. NO OTHER WARRANTY OR GUARANTEE OF ANY KIND IS MADE BY CARBOLINE, EXPRESS OR IMPLIED, STATUTORY, BY OPERATION OF LAW, OR OTHERWISE, INCLUDING MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. All of the trademarks referenced above are the property of Carboline International Corporation unless otherwise indicated. The whole text of this Product Data Sheet, as well as the documents derived from it, have been written in English, and for legal purposes the English version shall prevail.