



SOUTHWEST TYPE 5GP™

SIMPLIFIED YIELD CHART – INJECTED

Simplified Target

Yield: **43.7 BF/BAG (4.06 m2)**

	TARGET	RANGE	UNIT
ACCELERATOR A-20	1260	1250 – 1270	g/l
WATER	8.5	8.0 – 9.0	gal/bag
NOZZLE DENSITY	533	514 – 551	g/l

HOLD POINT: Yields measured in excess of 45.1 BF/Bag will result in dry densities below the minimum 15 PCF as published in the Underwriters Laboratories Inc.® Fire Resistance Directory.

Simplified Range (Carboline recommends nozzle yields be taken a minimum, 3 times per day. Carboline recommends the use of a 9/16 I.D orifice)

Yield (*)				8.0	US/G	8.5	US/G	9.0	US/G	9.5	US/G	10.0	US/G	Dry Density (PCF)
				30	L	32	L	34	L	36	L	38	L	
3.81	m ²	41.0	BF	547		567		586		606		626		16.5
3.93	m ²	42.3	BF	531		550		569		588		607		16.0
4.06	m ²	43.7	BF	514		533		551		569		588		15.5
4.19	m ²	45.1	BF	498		515		533		551		569		15.0

(*) Yield based on 1-inch (25.4mm) thickness. All weights shown are measured in grams. Cup weights are based on an actual 1000ml (1l) cup as supplied by Carboline (contact your local Carboline Fireproofing representative for cups).

Non-Carboline alternate cups can be purchased from major home improvement suppliers, these cups average 1038 ml when filled to the top. If utilizing these cups, multiply the cup weight by an average of 1.038 to provide accurate density/yield values.

Supplementary Information

Accelerator A-20 Mixing

(mix four 50 lb Bag/34 Gallons Water (total solution equals 44 gallons))

1. Mix accelerator A-20 as directed on the product data sheet. Allow bubbles in the solution to pop before checking density.
2. Use a 1-liter plastic container, place on scale and zero/tare container.
3. Fill the container level to the top with A-20 solution.
4. If weight is below 1265 g/l, add additional A-20 to mix until target is reached.
5. As an alternate to 1-3 above, place a hydrometer in the solution and determine the specific gravity.

Bags/HR	Accelerator A-20 Flow Rate (15 pcf)	
	Seconds to fill 1-liter cup	Alum. Pump Setting (%)
5	318	5
10	129	14
15	84	24
20	63	33
25	51	43
30	43	52

Nozzle Density

1. Set the accelerator flow rate to a quick dribble.
2. Commence spraying and pump for roughly 60 seconds until the system stabilizes.
3. After 60 seconds, spray TYPE 5GP directly into the Carboline 1000ml cup. Position the nozzle 12-18" above the cup and overfill.
4. Strike off any excess TYPE 5GP and level to the top of the container. Wait a further 60 seconds or until such time the material has stopped swelling. Again, strike level with the top of the container.
5. Place an empty container on the scale and press "on/tare"
6. Replace the tared container with the identical container, filled with TYPE 5GP and record the net weight.
7. Cross reference the above chart to determine yield and adjust injection flow rate as required.



SOUTHWEST TYPE 5GP™

SIMPLIFIED YIELD CHART – UN-INJECTED

Simplified Target

Yield: **31.4 BF/BAG (2.91 m2)**

	TARGET	RANGE	UNIT
WATER	8.5	8.0 – 9.0	gal/bag
NOZZLE DENSITY	741	716 - 767	g/l

Simplified Range (Carboline recommends nozzle yields be taken a minimum, 3 times per day. Carboline recommends the use of a 9/16 I.D orifice)

Yield (*)				8.0	US/G	8.5	US/G	9.0	US/G	9.5	US/G	10.0	US/G	Dry Density (PCF)
				30	L	32	L	34	L	36	L	38	L	
2.29	m ²	24.6	BF	911		944		976		1009		1041		28.0
2.47	m ²	26.5	BF	846		876		906		937		967		26.0
2.67	m ²	28.8	BF	781		809		837		865		893		24.0
2.91	m ²	31.4	BF	716		741		767		793		818		22.0

(*) Yield based on 1-inch (25.4mm) thickness. All weights shown are measured in grams. Cup weights are based on an actual 1000ml (1l) cup as supplied by Carboline (contact your local Carboline Fireproofing representative for cups).

Non-Carboline alternate cups can be purchased from major home improvement suppliers, these cups average 1038 ml when filled to the top. If utilizing these cups, multiply the cup weight by an average of 1.038 to provide accurate density/yield values.

Supplementary Information

Nozzle Density

1. Spray un-injected TYPE 5GP directly into the Carboline 1000ml cup. Position the nozzle 12-18" above the cup and overfill.
2. Strike off any excess TYPE 5GP and level to the top of the container.
3. Place an empty container on the scale and press "on/tare"
4. Replace the tared container with the identical container, filled with TYPE 5GP and record the net weight.
5. Cross reference the above simplified range to determine yield and adjust water, mixing time and/or air pressure accordingly.

Calculation

To calculate yield, follow the formula noted below:

$$\text{Yield} = 12 \times (\text{Gallons H}^2\text{o/Bag} \times 8.34 + \text{Bag Weight}) / \text{Nozzle Density}$$

To convert g/L to pcf for Nozzle Density, follow the formula below:

$$\text{g/L} \times 0.06243$$