

SELECTION & SPECIFICATION DATA

Generic Type	Two component solvent-free epoxy
Description	Epoxy patching and surfacing compound that exhibits excellent bond strength and chemical resistance to a variety of acids, alkalis, salt solutions and oils. It is used to fill voids and bugholes in precast or poured-in-place concrete and other masonry surfaces. Repairs damaged concrete, fills narrow cracks, and can be used as a coving material for floor-wall transitions or lap joint areas. May also be used to repair weld seams and pits in metal for potable water service with a compatible ANSI/NSF 61 approved lining.
Features	<ul style="list-style-type: none"> • Solvent free • Excellent film strength, abrasion, and impact resistance • Rapid hardening for quick service • Easy to mix ratios • Excellent film build and working properties
Color	Light Grey
Primer	Normally self-priming to steel, concrete or masonry surfaces. May be applied over other epoxies.
Dry Film Thickness	125 mils (3175 microns) per coat As required to fill the void or resurface the substrate. May be applied up to 1/8 inch (125 mils) per application on a vertical surface. Thicknesses greater or less than this will alter the coverage rate. Please consult Technical service for additional information.
Solids Content	By Volume 100% +/- 2%
Theoretical Coverage Rate	1604 ft ² /gal at 1.0 mils (39.4 m ² /l at 25 microns) 13 ft ² /gal at 125.0 mils (0.3 m ² /l at 3125 microns) Allow for loss in mixing and application.
VOC Values	As Supplied : 0 lbs/gal (0 g/l) (Calculated)
Dry Temp. Resistance	Continuous: 250°F (121°C) Non-Continuous: 300°F (149°C) Discoloration may be observed above 200 °F (93 °C).
Limitations	Epoxies may lose gloss, discolor and chalk when exposed to sunlight.
Topcoats	May be coated with Epoxies or Polyurethanes depending on exposure and need.

SUBSTRATES & SURFACE PREPARATION

General	All surfaces must be clean, dry and free of oil, grease, loose mill scale, dirt, dust or other materials which would impair the bond of the coating to be applied to the substrate in accordance with SSPC-SP 1. Surface preparation must meet the requirements of the coating being used.
Steel	Cleanliness: SSPC-SP10 Surface Profile: 1.5-3.0 mils (38-75 microns)

SUBSTRATES & SURFACE PREPARATION

Galvanized Steel	Clean to remove all contaminants and prepare in accordance with SSPC-SP 16 (1.5 to 3 mils/38-75 microns).
Concrete or CMU	Concrete must be cured 28 days at 75 °F (24 °C) and 50% relative humidity or equivalent. Prepare surfaces in accordance with ASTM D4258 Surface Cleaning of Concrete and ASTM D4259 Abrading Concrete. <u>Mortar joints</u> should be thoroughly cured for a minimum of 15 days at 75 °F (24 °C) and 50% relative humidity or equivalent.

PERFORMANCE DATA

All test data was generated under laboratory conditions. Field testing results may vary.

Test Method	System	Results
Bond Strength Elcometer (ASTM D4541)	Carboguard 501 over concrete	>400 psi concrete failure
Compressive Strength (ASTM C579)	Carboguard 501	5000 psi
Flexural Strength (ASTM C580)	Carboguard 501	2200 psi
Hardness Shore D Durometer (ASTM D2240)	Carboguard 501	60
Tensile Strength (ASTM C307)	Carboguard 501	1300 psi

Test reports and additional data available upon written request.

MIXING & THINNING

Mixing	Power mix separately and then combine and power mix for at least two minutes or until a uniform gray color is achieved. Recommend using a heavy-duty, slow speed drill and a jiffy mixer. When mixing partial kits it is critical to apportion equal volumes of the two components to ensure proper cure and film properties. Any unused material must be resealed immediately.
Ratio	1:1 Ratio (A to B)
Pot Life	15-30 min at 75 °F (24 °C) depending on volume mixed. Pot life ends when coating becomes too viscous to use. Pot life times will be less at higher temperatures or larger mixed masses.

APPLICATION EQUIPMENT GUIDELINES

Listed below are general equipment guidelines for the application of this product. Job site conditions may require modifications to these guidelines to achieve the desired results.

Hand Tools	This is a high solids thixotropic coating that is applied through the use of one or more of the following: steel finishing trowel, taping knife, spatula, or rigid squeegee. Use the surrounding area as a leveling guide for finishing.
-------------------	--

APPLICATION CONDITIONS

Condition	Material	Surface	Ambient	Humidity
Minimum	55°F (13°C)	55°F (13°C)	55°F (13°C)	0%
Maximum	90°F (32°C)	125°F (52°C)	110°F (43°C)	80%

This product simply requires the substrate temperature to be above the dew point. Condensation due to substrate temperatures below the dew point can cause flash rusting on prepared steel and interfere with proper adhesion to the substrate. Special application techniques may be required above or below normal application conditions. It may be sanded 8 to 16 hours after application, depending on ambient conditions.

CURING SCHEDULE

Surface Temp.	Set Time to Topcoat with Other Finishes	Ultimate Physical Characteristics
75°F (24°C)	8 Hours	7 Days

Higher film thickness, insufficient ventilation or cooler temperatures will require longer cure times. Excessive humidity or condensation on the surface during curing can interfere with the cure, can cause discoloration and may result in a surface haze. Any haze or blush must be removed by water washing before recoating. During high humidity conditions, it is recommended that the application be done while temperatures are increasing. ***Maximum recoat/topcoat times are 30 days for epoxies and 90 days for polyurethanes at 75°F (24°C).** If the maximum recoat times have been exceeded, the surface must be abraded by sweep blasting or sanding prior to the application of additional coats. Elastomeric topcoats (ie: Reactamine 760) require abrasively blasted 501 prior to topcoat.

CLEANUP & SAFETY

Cleanup	Use scouring pads and water or Thinner 2. In case of spillage, absorb and dispose of in accordance with local applicable regulations.
Safety	Read and follow all caution statements on this product data sheet and on the SDS for this product. Employ normal workmanlike safety precautions. Use adequate ventilation. Keep container closed when not in use.
Caution	All electrical equipment and installations should be made and grounded in accordance with the National Electric Code. In areas where explosion hazards exist, workers should be required to use non-ferrous tools and wear conductive and non-sparking shoes.

PACKAGING, HANDLING & STORAGE

Shelf Life	Pt. A & B 24 months *Shelf Life: (actual stated shelf life) when kept at recommended storage conditions and in original unopened containers
Storage Temperature & Humidity	60-85 °F (16-30 °C) Do not freeze.
Storage	Store indoors
Shipping Weight (Approximate)	3.6 Gal. Kit 50 lbs (23 kg)
Flash Point (Setaflash)	Part A >267 °F (131 °C) Part B >485 °F (251 °C)

WARRANTY

To the best of our knowledge the technical data contained herein is true and accurate on the date of publication and is subject to change without prior notice. User must contact Carboline to verify correctness before specifying or ordering. No guarantee of accuracy is given or implied. Carboline warrants our products to be free of manufacturing defects in accord with applicable Carboline quality control procedures. THIS WARRANTY IS NOT VALID WHEN THE PRODUCT IS NOT: (1) APPLIED IN ACCORDANCE WITH CARBOLINE'S SPECIFICATIONS, AND/OR (2) PROPERLY STORED, CURED, AND USED UNDER NORMAL OPERATING CONDITIONS. Carboline assumes no responsibility for coverage, performance, injuries, or damages resulting from use of the product. If this product is found not to perform as specified upon inspection by a Carboline representative during the warranty period, Carboline's sole obligation, if any, is to replace the Carboline product(s) proven to be defective or refund the purchase price thereof, at Carboline's sole option. Carboline shall not be liable for any other losses or damages. This warranty excludes (1) labor and costs of labor for the application or removal of any product, and (2) any incidental or consequential damages, whether based on breach of express or implied warranty, negligence, strict liability or any other legal theory. NO OTHER WARRANTY OR GUARANTEE OF ANY KIND IS MADE BY CARBOLINE, EXPRESS OR IMPLIED, STATUTORY, BY OPERATION OF LAW, OR OTHERWISE, INCLUDING MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. All of the trademarks referenced above are the property of Carboline International Corporation unless otherwise indicated. The whole text of this Product Data Sheet, as well as the documents derived from it, have been written in English, and for legal purposes the English version shall prevail.